

BRAVEHEART - BRAVEHEART

Tariff item number 54076130	Launch date 01/09/2017	Delivery time special lab dip/sample (weeks) 2
--------------------------------	---------------------------	---

BASIC INFORMATION

Country of origin Belgium	Number of colour ways 34	Vertical repeat plain	Horizontal repeat plain
Average piece length (m) 40.0	Face in Yes	Minimum for special colour (m) 1000	

CATEGORY

Colouring type Piece dyed	Type of print/dye - vat Yes	After treatment - other specification brushed backing + FibreGuard
------------------------------	--------------------------------	---

Care codes



Use codes

Use code - upholstery Yes	Use code - bed covering Yes	Use code - accessories Yes
------------------------------	--------------------------------	-------------------------------

FABRIC TYPE

Composition 100% Polyester	Average yarn number 13.35	Composition fabric 100% Polyester	Composition backing 100% Polyester
Weaving type - plain Yes	Construction 32x21	Useable width (cm) 145	Useable width (inch) 57
Full width (cm) 147	Full width (inch) 57 3/4	Woven Yes	Weight (g/m ²) 397

FR STANDARDS

BS5852 source 0 Yes NFPA 260 Yes	BS5852 source 1 comment Yes, with FR coating	CAL 117 (Complies) Yes	FMVSS 302 (Pass) Yes
---	---	---------------------------	-------------------------

ENVIRONMENTAL STANDARDS

Oeko-Tex

SPECIFICATIONS

Martindale (rubs)	Colour fastness to wear	Colour fastness to light	Colour fastness to water
100,000	4	4-5	5
Colour fastness dry rub	Colour fastness wet rub	Pilling	Brush pilling
4-5	4-5	4	4
Wyzenbeek (rubs)	Wyzenbeek cotton duck type heavy upholstery		
135,000	Yes		

Tearing strength

ISO 13937-3

Tearing strength warp (N)	Tearing strength weft (N)
76	140

Tensile strength

ISO 13934-1

Tensile strength warp (N/5cm)	Tensile strength weft (N/5cm)
2000	780

Elongation

ISO 13934-1

Elongation warp (%)	Elongation weft (%)
42.5	33

Seam slippage

ISO 13936-2

Seam slippage warp (mm)	Seam slippage weft (mm)
3	2

Resistance to domestic washing 30°C (indicated in %)

ISO 6330

Dimensional change warp	Dimensional change warp after ironing	Dimensional change weft	Dimensional change weft after ironing
-0.63	-0.40	-0.30	-0.27

Colour fastness (ISO 105 C06)
4-5

Resistance to domestic washing 60°C (indicated in %)

ISO 6330

Dimensional change warp	Dimensional change warp after ironing	Dimensional change weft	Dimensional change weft after ironing
-2.30	-2.20	-1.17	-1.00

Colour fastness (ISO 105 C06)
4-5

Resistance to dry cleaning P (indicated in %)

ISO 105 D01

Dimensional change warp	Dimensional change warp after ironing	Dimensional change weft	Dimensional change weft after ironing
-1.92	-1.59	-0.70	-0.46

Colour fastness (ISO 105 D01)

Dimensional stability (indicated in %)

ISO 3759

Dimensional change warp +0.02	Dimensional change warp after ironing without steam +0.07	Dimensional change warp after ironing with steam +0.07	Dimensional change weft +0.00
Dimensional change weft after ironing without steam +0.13	Dimensional change weft after ironing with steam +0.47		

CONSTRUCTION

Yarn 1

Warp composition 100% Polyester		
Warp yarn sizes 380D	Warp threads per cm 32	Warp turns per meter (TPM) NA
Warp type man made Yes	Warp type filament Yes	
Warp specification carded Yes		

Yarn 2

Weft composition 100% Polyester		
Weft yarn sizes 380D	Weft threads per cm 21	Weft turns per meter (TPM) NA
Weft type man made Yes	Weft type filament Yes	
Weft specification carded Yes		